Patent Number(s): JP52129798-A

Title: Polyester prodn. esp. polyethylene terephthalate with fewer ether-gps. - by esterifying in the presence of e.g. titanium cpd. and then adding alkoxide of antimony and/or germanium and polycondensing

Patent Assignee Name(s) and Code(s): MITSUBISHI RAYON CO LTD (MITR-C)

Derwent Primary Accession Number: 1977-88839Y [50]

Patents Cited by Inventor: 0
Patents Cited by Examiner: 0
Articles Cited by Inventor: 0
Articles Cited by Examiner: 0
Articles Cited by Examiner: 0

Prodn. comprises continuously reacting a slurry of terephthalic acid contg. ethylene glycol in a molar ratio 1.05-1.8. Reaction is at 230-270 degrees C under atmospheric pressure - 7 kg/cm2-G until 80-94% of the residual gps. of acid remain. Reaction mixt is fed to a second reactor a d allowed to react at 250 degrees C -280 degrees C and atmospheric pressure -200 mmlg-ab until 8gt;95% of the residual acid gps. are esterified.

Esterification is conducted in the presence of 1 of Ti Mg and Co cpds. and then antimony alloxide and/or germanium alkoxide are added to the esterified material, followed by subjecting the whole mixture to polycondensation, to obtain the corresp. polyester. Process is esp, for prodn. of polyethylene terephthalate contg. relatively fewer ether-linkages with high whiteness.

International Patent Classification: C08G-063/22

Derwent Class: A23 (Polyamides, polyesters, polycarbonates, alkyds)
Derwent Manual Code(s): A02-A06; A02-A07; A02-A07A; A05-E04A

Detent Details

Patent Number	Publ. Date	Main IPC	Week	Page Count	Language
JP52129798-A	31 Oct 1977		197750		

Priority Application Information and Date:

JP047443 26 Apr 1976